

Material	Type	Structure	Composition		Type of lubrication	Maxi specific load MPa	Form	Comments
			Support	revêtement				
CSB-50		Plain multi-layers	Steel + porous bronze	PTFE + MoS ₂	Dry	250	Wrapped bearing	Low coefficient of friction
CSB-11		Plain multi-layers	CuSn8 + porous bronze	PTFE + MoS ₂	Dry	250	Wrapped bearing	Low coefficient of friction
CSB-80		Indented multi-layers	Steel + porous bronze	POM Acetale resin	lubricated	250	Wrapped bearing	Good resistance with high temperature
CSB-TEX	CSB-TEX3	Plain multi-layers	Stainless steel	PTFE fibres fabric overlay	Dry	350	Wrapped bearing	Good resistant under high load and pollution
	CSB-TEXB	Plain multi-layers	CuSn8	PTFE fibres fabric overlay	Dry	350	Wrapped bearing	Good resistant under high load and pollution
CSB-CRG		Plain mono-layer	Epoxy resin + GF	PTFE and PBT fibers + solid lubricant	Dry	240	Massive bearing	Good resistance under high and shock loads and pollution
CSB-850	BM3	Plain multi-layers	Aisi 316	CuSn12 sinter + PTFE + graphite	Dry	150	Wrapped bearing	GALL Chain
	BM4	Plain multi-layers	Bronze	CuSn12 sinter + PTFE + graphite	Dry	100	Wrapped bearing	GALL Chain
	S	Plain multi-layers	Carbon steel	Copper nickel alloy + graphite	Dry	100	Wrapped bearing	Wear and pollution resistant
CSB-EP	4	Plain mono-layer	Thermoplastic + additives		Dry	120	Massive bearing	Green Chain